

## TECHNICAL DATA SHEET

### ITEM : STRAITO

#### SURFACE AND APPLICATION REQUIREMENT :

New smooth, regular and non - absorbent plasters, surfaces without undulations do not need any special preparation. Such surfaces shall need a two coat application by brush.

During application the surface should be well protected from strong winds, hot sun and cold weather. Application should be carried out at a temperature over 5°C. The product is rain proof after eight hours and touch dry after one hour at a temperature of 20°C. The application equipment used should be immediately washed with water.

#### SPECIFICATIONS :

|    |                    |   |
|----|--------------------|---|
| A. | Surface Required   | Plain, cement sand / stone dust, plaster, gypsum, plywood surfaces etc.                                   |
| B. | Application        | By Special tools and top coat by brush  |
| C. | Film Thickness     | Upto 2 mm.  |
| D. | Consumption Rate   | 2.00 Kg. Per Sq. Mtr. (approx.) – of base material<br>0.30 Kg. Per Sq. Mtr. (approx.) – Top Coat material |
| E. | Average Shade Life | Upto 10 Years – except blue & green families which comparatively fade faster .                            |
| F. | Adhesion           | Virtually Permanent   |
| G. | Textures           | Strait comb like  |

#### DETAILS FOR ADOPTION AS TENDER ITEM :

Providing and applying acrylic aggregate textured wall coating in Spectrum Straito finish in shade No. \* maintaining material consumption rate of average 2 Kg. per m<sup>2</sup> for the base items and 0.3 Kg. top and approx. 2 mm. microns thickness on new walls in the exterior of the building. Undulations, broken edges, minor imperfections / irregularities should be rectified by using a paste made of Spectrum Rectochem Surface Improver mixed with ordinary portland cement in the ratio of 1:1. Old, flaking, plaster of paris, gypsum and highly absorbent surfaces and those already finished with lime or distemper should be brushed down and then treated with a coat of Spectrum Prime Coat diluted with water in the ratio 1:1 and applied by a brush.

\* Mention required shade number from shade card.